

Gyproc CreteStone Plaster

Gyproc CreteStone – Skimming Plaster

Gyproc CreteStone is a skim finishing plaster applied with a skim application method, by using a steel trowel. CreteStone is suitable as a skim finishing plaster for application onto low suction-concrete soffits, concrete pre-cast blocks and Gyproc RhinoBoard.



Mixing instructions

- 1** Use cold clean water only.
- 2** Do not add any foreign matter.
- 3** Soak for 10 minutes.
- 4** Mix slowly until there are no lumps. Do not over stir. Do not mix with your hands.
- 5** Clean tools and mixing container after each mix.
- 6** Do not mix more CreteStone than you can use in 1 (one) hour.

Note: Should not be sanded.

Application instructions

1. Do not apply when temperature is below freezing.
2. Surfaces to be clean and dust free before application.
3. For internal use only.
4. Please consult your paint vendor/manufacturer on the correct primer for application onto Gypsum surfaces.
5. Application of epoxy paint is not recommended.
6. Not for human consumption.
7. For detailed application refer to Gyproc Plaster Guide Booklet or contact the Customer Contact Centre 0860 27 28 29.
8. Store inside on a level surface, off the floor, in a dry place protected from the weather.




Tools for application

Mixing bucket



Hawk



Steel trowel




Covering capacity

Applied 6mm thick the coverage will be approximately 11.5m²/40kg

N.B. Gypsum plaster should be stacked on a level surface in a dry place, preferably inside a building and properly protected from damp and inclement weather. If gypsum is to be stacked on a concrete floor inside a building, a damp roof membrane should first be laid down, or it should be stacked on a timber pallet.

For interior use only.



11.5m² at thickness of 6mm